

PATENT ABSTRACTS OF JAPAN(11)Publication number : **08-038910**(43)Date of publication of application : **13.02.1996**

(51)Int.Cl.

B01J 31/10
B01J 39/20
// C07B 61/00
C07C 37/20
C07C 39/16(21)Application number : **06-178638**(71)Applicant : **MITSUBISHI CHEM CORP**(22)Date of filing : **29.07.1994**(72)Inventor : **SUGAWARA TAKAHIRO**
WATANABE MICH
SHIRASAKI YOSHIKAZU
SUZUKI TOSHITAKA**(54) ION EXCHANGE RESIN**

(57)Abstract:

PURPOSE: To produce bisphenol-A by condensation reaction of acetone and phenols which gives a high conversion rate of acetone and is economically advantageous by producing ionic bonds of N,N,N-triethyl-3-mercaptopropyl ammonium.

CONSTITUTION: This strong acid sulfonic acid-type ion exchange resin is prepared by producing ionic bonds of N,N,N-triethyl-3-mercaptopropyl ammonium. To bond N,N,N-triethyl-3-mercaptopropyl ammonium to the sulfonic acid groups of the strong acid ion exchange resin, for example, the counter anion of N,N,N-triethyl-3-mercaptopropyl ammonium dissolved in ion-exchanged water is preliminarily converted into anions which can easily exchange ions with sulfonic acid anion such as acetate anion, carbonate anion, then the soln. is added to the strong acid ion exchange resin dispersed in ion-exchanged water and stirred for 0.1 to 2 hours.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office